Preferred citation: G.A. Baum, C.C. Habeger and E.H. Fleischman. Measurement of the orthotropic elastic constants of paper. In The role of fundamental research in paper-making, *Trans. of the VIIth Fund. Res. Symp. Cambridge, 1981*, (Fundamental Research Committee, ed.), pp 453–478, FRC, Manchester, 2018. DOI: 10.15376/frc.1981.1.453.

MEASUREMENT OF THE ORTHOTROPIC ELASTIC CONSTANTS OF PAPER

G. A. Baum, C. C. Habeger, E.H. Fleischman The Institute of Paper Chemistry. Appleton, Wisconsin, USA

Abstract

A wave theory describing paper as a three-dimensional homogeneous orthotropic plate is discussed, and the theory compared with experiment. The results indicate that as long as the wavelength is large compared to typical fibre dimensions, paper may be considered to behave as a homogeneous orthotropic plate. This allows determination of all nine orthotropic elastic constants.

Measurement of the three Young's moduli, the in-plane shear modulus, and the in-plane Poisson's ratios were made as functions of fibre orientation, wet straining, and density. Qualitatively, the results show that a variable producing a change in properties in one direction, alters the properties in the other two directions in a predictable way. The in-plane shear modulus and the Poisson's ratios, expressed as $(v_{xy}v_{yx})^{1/2}$ were found to be relatively insensitive to fibre orientation and wet straining, except at the highest levels of each.

Introduction

Paper is a layered structure which is highly anisotropic. In the plane of the paper, Young's modulus in the machine direction is typically twice that in the cross-machine direction. This anisotropy results from increased fibre orientation in the machine direction as well as the effect of drying restraints in this direction. The out-of-plane, or z-direction, Young's modulus, is considerably smaller than the in-plane values, presumably because of the layered structure.

453

Taken together, the above observations suggest that paper may be described as a three dimensional orthotropic material, that is a material having three mutually perpendicular symmetry planes. The directions normal to these planes would be the machine direction (MD), cross-machine direction (CD), and the thickness direction (ZD). An orthotropic material is characterised by nine independent elastic constants: three Young's moduli, three shear moduli, and three Poisson's ratios.

This article demonstrates that paper may be considered a three-dimensional orthotropic material as far as wave propagation techniques are concerned, and discusses how the orthotropic elastic constants can be measured. These constants are examined with respect to the effects of machine and process variables.

Wave Propagation in Paper

In an isotropic material of infinite extent, two types of wave motion can exist. These are longitudinal (or dilatational) modes, in which the particles composing the material are displaced parallel to the direction of wave propagation, and shear (or distortional) modes in which the particles are displaced perpendicular to the direction of propagation. Longitudinal modes travel faster than shear modes. Both types of waves are non-dispersive, that is, the velocity of the wave is not a function of frequency.

If either mode is reflected from a free boundary, however, partial mode conversion occurs. The boundaries in the ZD of paper, for example, couple the two types of waves such that pure bulk modes do not exist (except a shear mode polarised in the plane of the sheet). An otherwise infinite material that is finite in one dimension is called a plate. It will be shown that paper can be considered a plate-like material as far as elastic wave propagation is concerned.

Wave Propagation in Infinite Media

Before turning our attention to orthotropic plates (i.e. paper), it will be beneficial to consider wave propagation in an infinite orthotropic medium. For such a material the stresses, t_{ij} , can be expressed in terms of the strains, e_{ij} , by

^τ 11	=	$C_{11}e_{11} + C_{12}e_{22} + C_{13}e_{33}$	
τ ₂₂	=	$C_{12}e_{11} + C_{22}e_{22} + C_{23}e_{33}$	
τ33	=	$c_{13}e_{11} + c_{23}e_{22} + c_{33}e_{33}$	
τ23	=	2C ₄₄ e ₂₃	(1)
^τ 13	=	^{2C} 55 ^e 13	
^τ 12	=	^{2C} 66 ^e 12	

The nine elastic stiffnesses, C_{ij} have units of stress (Pa).

In paper we assume the MD, CD, and ZD are the three principal directions of symmetry, 1, 2, and 3, respectively. The strains may be defined in terms of the particle displacements from equilibrium by

$$e_{ij} = (U_{i,j} + U_{j,i})/2, \quad i,j = 1,2,3$$
 (2)

where $U_{i,j} = \partial U_i / \partial X_j$.

The equations of motion for mechanical disturbances in an elastic medium are

$$\sum_{j=1}^{3} \tau_{ij,j} = \rho \ddot{U}_{i}$$
(3)

where ρ is the mass density of the medium and $\ddot{U}_i = \partial^2 U / \partial t^2$.

Substitution of equations (1) and (2) into (3) yields,

$$\begin{split} &\rho U^{1=C}{}_{11} U_{1,11}^{+C}{}_{12} U_{2,12}^{+C}{}_{13} U_{3,13}^{+C}{}_{55}^{-}(U_{1,33}^{+U}{}_{3,31}^{+C}{}_{66}^{-}(U_{1,22}^{+U}{}_{2,21}^{+U}{}_{2,21}^{+U}{}_{2,23}^{+U}{}_{3,32}^{+C}{}_{66}^{-}(U_{1,12}^{+U}{}_{2,11}^{+U}{}_{2,11}^{+U}{}_{2,11}^{+U}{}_{2,23}^{+U}{}_{3,22}^{+C}{}_{55}^{-}(U_{1,13}^{+U}{}_{3,11}^{+U}{}_{3,11}^{+U}{}_{2,23}^{+U}{}_{3,22}^{+C}{}_{55}^{-}(U_{1,13}^{+U}{}_{3,11}$$

where $U_{i,jk} = \partial^2 U_i / \partial X_j \partial X_k$.

Plane waves are solutions to these equations,

$$U_{i} = U_{i0} \exp(i(K_{x}X_{1} + K_{y}X_{2} + K_{z}X_{3} - \omega t))$$
(5)

where U_{i0} is the oscillation amplitude, K_x , K_y , and K_z are the components of the wave-vector <u>K</u>, ω is the angular frequency, and i is the square root of -1.

Solving equations (4) gives the elastic stiffnesses of the material in terms of measurable velocities. For example, for the infinite orthotropic material, the propagation of longitudinal modes along the three principal directions would give

$$V_{Lx} (= \omega/K_x) = (C_{11}/\rho)^{1/2}$$

$$V_{Ly} (= \omega/K_y) = (C_{22}/\rho)^{1/2}$$

$$V_{Lz} (= \omega/K_z) = (C_{33}/\rho)^{1/2}$$
(6)

While the propagation of shear modes along the principal directions would give in the yz, xz, and xy planes.

$$V_{Syz} = (C_{44}/\rho)^{1/2} V_{Sxz} = (C_{55}/\rho)^{1/2}$$
(7)
$$V_{Sxy} = (C_{66}/\rho)^{1/2}$$

The relationships between velocities and the off-diagonal elastic stiffnesses C_{12} , C_{13} , and C_{23} (see equation (1)), involve the propagation of waves not along the principal directions, and are, therefore, more complicated than equations (6) and (7) above.

456

The determinations of these for paper fall outside the scope of infinite media theory and have been discussed $elsewhere^{(5)}$.

For orthotropic bulk waves travelling in principal directions the particle displacements are normal or parallel to the propagation direction and the waves are not dispersive. In the more general case in which the direction of propagation is not along a principal direction, the particle displacements are not parallel or perpendicular to the propagation direction⁽¹⁾. These waves are still not dispersive, but the velocity and the angle between the wave vector and the polarisation depend on the propagation direction.

Plate Wave Theory Applied to Paper

Because paper is very thin it cannot be described in terms of an infinite medium model. It is reasonable to assume that we must treat it as a plate. A detailed description of the appropriate theory has been presented elsewhere⁽²⁾. The basic elements can be understood by reference to figure 1.



Fig 1-Construction of orthotropic plate waves from four orthotropic bulk waves. Wave vectors are shown.

The normal modes of oscillation in a plate can be expressed as the sum of two shear waves and two longitudinal waves. All four bulk waves have the same vector projected along the plate, but the transverse components are positive for one pair of shear

458 orthotropic elastic constants of paper

and longitudinal waves, and negative for the other pair. The magnitudes and directions of the waves are chosen so that the free boundary conditions are met at the plate surfaces. Since the shear wave is slower, its direction of propagation is nearer the plate normal. Along the plate, the plate waves are plane waves with phase velocity equal to the angular frequency divided by the component of the bulk wave vector along the plate. As the frequency changes, a corresponding change in direction of the bulk waves is required in order to satisfy the boundary conditions. Plate waves, then, are dispersive: the velocity is a function of frequency. Plate waves are described as symmetric or antisymmetric, depending on the symmetry about the midplane of the particle displacement along the plate, as shown in figure 2.



a. Symmetric mode



b. Antisymmetric mode

Fig 2-Two types of plate modes.

A test of the orthotropic plate wave theory⁽²⁾ was carried out by performing the following steps.

(1) The bulk orthotropic elastic constants, as defined by equations (6) and (7) were measured for paper using specially constructed samples which approximated to the infinite media requirement. The off-diagonal stiffnesses C_{13} and C_{23} were obtained using relationships obtained from orthotropic plate wave theory in the limit as frequency goes to zero and C_{12} was found by propagating a shear wave at 45° to the MD in the MD-CD plane⁽³⁾. Measurement of the bulk elastic constants required a number of different transducer-specimen configurations as indicated in figure 3.





Fig 3—Transducer-specimen configurations for bulk wave measurements. (a) Z-direction, L or S. (b) MD or CD measurements, L or S. (c) MD or CD measurement, L or S. T = transmitter, R = receiver, L = longitudinal, S = shear.

460 orthotropic elastic constants of paper

(2) The orthotropic elastic constants determined in Step 1 were used in the plate wave theory to predict the dispersion curves relating phase velocity and frequency. Figure 4 shows dispersion curves for the ZD-MD and ZD-CD planes of a chip board sample.



Fig 4—Orthotropic plate wave for the ZD–MD plane (A) and ZD–CD plane (B). First three modes shown for each. Calculated using measured bulk orthotropic elastic constants. (A) $C_{11}/\rho = 10.2$, $C_{13}/\rho = 0.32$, $C_{33}/\rho = 0.08$, $C_{55}/\rho = 0.22$, all in (mm/µsec)². (B) $C_{22}/\rho = 3.47$, $C_{23}/\rho = 0.25$, $C_{33}/\rho = 0.08$, $C_{44}/\rho = 0.16$, all in (mm/µsec)². Chipboard specimen of thickness 0.75 mm.

The rapid drop of the zeroth order symmetric, S_0 , mode velocity with frequency results from the extremely low value for the measured z-direction stiffness, C_{33} . If this number increased, the drop off would occur at higher frequencies, the higher order modes would begin to propagate at higher frequencies, and the A_0 mode would reach a plateau at higher frequencies. An

interesting result is the development of `plateaux' in the higher order symmetry modes. These are nearly nondispersive regions at approximately the same velocity as the low frequency S_o mode.

(3) final test of the theory and the validity of the The measurements of bulk orthotropic elastic constants was performed by measuring plate wave velocities as a function of frequency directly on the paper-board sample The method of Luukkala et al.(4) was used in which a non-contacting ultrasonic transmitter is used to excite plate modes in the paper. At certain combinations of frequency and orientation of the transmitter, plate waves are excited and a receiver located behind the paper and opposite the transmitter records a maximum signal. The frequency and angular orientation of the transmitter with respect to the paper allow the plate wave velocities to be calculated. These plate velocities can be compared to the plate velocities predicted from theory and bulk constants. Figure 5 shows such a comparison for carton stock.



Fig 5—Comparison of measured plate wave velocities ($^{\circ}$ Specimen 1 and \bullet Specimen 2) with curves predicted from theory and using bulk wave velocities measured on same material.

462 orthotropic elastic constants of paper

Although the data falls in narrow frequency windows (because of limitations due to the air), the agreement between `experiment' and `theory' is very good. The good agreement leads to the following conclusions concerning wave theories applied to paper.

- . Paper behaves as a homogeneous continuum,
- . The orthotropic description of paper is valid, and
- . The bulk orthotropic constants form a self consistent set.

Subsequent study has verified the existence of the plateaux⁽⁵⁾ and led to alternative means of determining the constants C_{11} and C_{22} . The nine orthotropic elastic constants for the carton stock mentioned above have been presented elsewhere⁽⁵⁾.

Limitations of the Application of Plate Wave Theory to Paper

There are several important limitations on the theory. Firstly, it will not apply for all wavelengths. As the frequency increases the wavelength becomes shorter. When the measuring wavelength becomes comparable to the fibre dimensions the theory is no longer applicable. This occurs in the vicinity of 2 MHz. Secondly, the theory was developed for an elastic material, while paper is known to be visco-elastic⁽⁶⁾. Although a visco-elastic theory would be desirable, the present theory is capable of providing information on elastic response that cannot be found via the more usual mechanical test methods. Finally, as in any wave phenomenon, interference and diffraction effects may occur which can cause experimental difficulties. In this work we found that measurement schemes in which the transducers are closer than approximately one-half wavelength result in undesirable effects. ZD measurments are especially susceptible to such errors because paper is so thin. The errors depend inversely on the paper thickness and measuring frequency. Above approximately 0.5 mm, at 1 MHz, the error is negligible.

Orthotropic Elastic Constants of Paper

The application of ultrasonic techniques to determine the orthotropic elastic constants of paper is part of a fundamental research programme in our laboratory. Initial efforts centered on measuring the in-plane (MD-CD) elastic constants of handsheets and machine-made paper. The in-plane constants, in engineering terminology⁽⁹⁾, are the two Young's moduli, E_x and E_y , the shear modulus, G_{xy} , and the Poisson's ratios, v_{xy} and v_{yx} .

Since $\vee_{yx} = \vee_{xy} E_x / E_y$ there are only four independent constants. Some of this work has been described elsewhere^(7,8).

Measurements on Mechanically Strained Sheets

The theoretical relationships between ultrasonic velocities and the elastic moduli of paper have been developed for unstrained sheets, and all of our reported laboratory results are for measurements on unstrained sheets. The effects of straining the sheet on the in-plane velocities, however, have been studied, and the results are presented here.

Ultrasonic velocities were measured during mechanical loadelongation tests and during long term stress relaxation. The experiments were carried out on 305mm (CD) by 2m (MD) samples of a bleached ledger paper of basis weight 79 g/m². The IPC large scale tensile tester was used to apply uniaxial MD stresses and record the load-elongation behaviour. Tests were conducted at relative humidities of 15, 48, 66, and 80%, all at 22.8°C. At each humidity the samples were strained to about 80% of their ultimate tensile strength in four approximately equal stress increments. The ultrasonic velocities for longitudinal and shear waves were measured at each increment for both the MD and CD (V_{Lx}, V_{sx}, V_{Ly}) . These measurements were repeated as the specimen was unloaded in four increments. The time required for the measurements at each stress increment was about 60 seconds, and of course stress relaxation did occur in this time.

Stress relaxation effects were investigated by stressing the specimens to 80% of ultimate strength, maintaining the strain, and measuring the ultrasonic velocities after times of 1, 22, 90, 162, and 430 hours (all at 48% RH, 22.8°C). Because more time was available for these measurements, they were performed in the usual manner in which a relatively large area of the specimen is examined⁽⁸⁾.

The essential results for the load-elongation studies and the stress relaxation studies are given in Tables 1 and 2, respectively.

RH,	Load,	Strain,	V/Vo ⁽⁺⁾	V/Vo	V/Vo
%	N	%	MD	CD	
			Longitudinal	Longitudinal	Shear
15	712	0.46	1.026 (.14)	0.998 (.014)	1.012 (.011)
48	712	0.72	1.020 (.030)	0.994 (.014)	1.013 (.011)
66	623	0.74	1.037 (.010)	0.991 (.014)	1.010 (.014)
80	534	0.98	1.062 (.016)	0.981 (.010)	1.010 (.011)

* About 80% of failure load. Numbers in parentheses are standard deviations.

 $^{(+)}V_{o}$ are the velocities at zero stress and zero strain for each direction and wave type at each RH condition.

Table 1

Ultrasonic Velocities at Maximum Load* for Mechanically Strained Specimens

464

In Table 1, conditions at the maximum loads only are shown for each of the relative humidities. The greatest effect is on the MD longitudinal velocity at 80% RH, where the velocity has <u>increased</u> over 6%. At this point the tangent modulus from the load-elongation curve has <u>decreased</u> to about one-third its original value. Thus even though the samples are not behaving elastically in the mechanical measurements, the ultrasonic velocities differ from their unstrained values by a few percent. The effect on the other two velocities is considerably smaller.

Time	Load	Strain,	Veloc	ity Ratios, V/V*	
hrs,	N	%	MD	CD	
			Longitudinal	Longitudinal	Shear
1	489-520	.61	1.051	0.999	1.010
22	425-431	.61	1.046	0.989	1.009
90	387-391	.61	1.042	1.002	1.009
162	391	.61	1.045	0.994	1.006
430	351	.61	1.039	0.997	1.009

 V_{o} are the velocities at zero strain and zero stress. All measurements at 48% RH, 22.8⁰C.

Table 2

Velocity Ratios During Stress Relaxation

From Table 2 it can be seen that the effect of stress relaxation at constant strain is very small for V_{Lx} . Velocity changes due to stress relaxation were less than 1.2% over the 430 hour experiment, while the load decreased over 30%. Velocities V_{Ly} and V_{Sx} or V_{Sy} were not appreciably affected by the stress relaxation phenomena.

465

466

Taken together, the above results suggest that the mechanisms governing the stress-strain relationship at high frequecies are largely independent of the relatively long time phenomena exhibited in the usual stress-strain response. That is, (except for corrections of the order of the strain) ultrasonic and mechanical deformations superimpose linearly even as mechanical failure is approached. Similar results are found for high frequency mechanical cycling about a point on the stress-strain curve in the plastic regime, although in that case the measured modulus would be less than in the ultrasonic case.

Effect of Fibre Orientation and Wet Straining on Elastic Properties

With increasing confidence in determining the elastic constants of paper by ultrasonic pulse propagation techniques, it was decided to use this new tool to explore the effects of certain paper-making variables. In particular, the effects of fibre orientation and wet straining (drying restraint) on the measured elastic constants were investigated.

The final properties of paper made from a given furnish can be altered quite dramatically by varying the fibre orientation in the plane of the sheet, and/or varying the restraint imposed on the sheet as it dries. The effects of these, individually or together, on the mechanical properties of paper have been the subject of many published articles (10-22). Due to limitations of available testing methods, however, all of these studies were concerned with the in-plane characteristics of the sheet. Most investigations were concerned with only two of the four in-plane elastic constants of paper, namely, Young's modulus in the machine and cross-machine directions.

Our objective was to obtain data showing the effects of fibre orientation and drying restraint on all four of the in-plane elastic moduli (E_x , E_y , G_{xy} , and V_{xy}). Furthermore, because there is a growing awareness that paper must be considered a three-dimensional material, a second objective was to investigate the

effects of in-plane fibre orientation and drying restraints on the ZD elastic stiffness, C_{33} . One conclusion of our earlier experimental work was that the out-of-plane elastic constants of paper could be accurately determined, provided that the sheet thickness is greater than about 0.5 mm.

Three sets of sheets were prepared, one set of random (nonorientated) handsheets and two sets of orientated sheets. All were made from a bleached western softwood kraft pulp, obtained in dry-lap form. Prior to sheet forming, the pulp was soaked, defibred, and beaten in a laboratory Valley beater to a freeness of approximately 500 C.S.F. The random sheets were formed on an 8 inch square Noble and Wood sheet mould and the orientated sheets were formed on a `Formette Dynamique' sheet machine made by Allimand^(23,24). The Weyerhaeuser Company generously allowed the used of their machine for making the orientated sheets. Two degrees of fibre orientation, designated as `low' and `high', were achieved by appropriate adjustments of the stock jet velocity and wire speed on the Formette.

Since accurate z-direction measurements require thick sheets, all of the sheets were formed with a basis weight around $400g/m^2$. Such heavy sheets can be formed in a single layer on the Formette with little difficulty. The random handsheets, however, were formed by wet pressing together six sheets, each with a basis weight of about 65 g/m², in order to obtain more uniform sheet properties at the required basis weight.

It is well known from a theoretical as well as a practical standpoint, that paper properties vary considerably as a function of the final apparent bulk density of the sheet. Since process conditions, adjusted to produce sheets with different fibre orientations and drying restraints, often result in changing the apparent density as well, it was necessary to include apparent density as a variable. The apparent density was varied by applying different wet pressing pressures with a platen type press.

After wet pressing, the sheets were dried under one of three levels of controlled restraint. The lowest level involved clamping the sheet biaxially using two pairs of clamps and drying it without allowing any dimensional change. For the medium and high levels of restraint, the sheet was clamped in the direction of preferred fibre orientation (hereafter referred to as the MD) and then strained while still wet to about 1.2% or 2.4% strain, respectively, at a rate of about 0.8%/min. When strained in the machine direction, the wet sheet contracted in the cross direction. After wet straining, the sheet was also clamped in the cross direction, allowing no further dimensional change during drying.



Fig 6-Young's modulus in the MD, E_X , as a function of apparent density at different fibre orientations and wet straining levels.

The in-plane elastic constants and the z-direction stiffness were determined by ultrasonic techniques as discussed earlier. In addition, Young's moduli in the machine and cross-machine directions were determined mechanically on the Instron Universal

468

Testing Machine. The tensile strengths in the machine, crossmachine and z-direction were also measured.

The dependences of the machine direction Young's modulus determined ultrasonically on fibre orientation, wet straining, and apparent density are shown in figure 6. The three solid lines correspond to the three different fibre orientations with no wet straining. The lowest solid line is for the random handsheets while the uppermost solid line corresponds to the most orientated sheets. The dashed lines correspond to the maximum wet straining. Fibre orientation has a rather dramatic effect on the modulus, incrasing it by about 70% over the range investigated. Wet straining has a significant but smaller effect. At each fibre orientation level, wet straining increased the modulus an additional 25%. As more fibres are orientated in the machine direction, the CD Young' modulus decreases quite significantly, as shown in figure 7.



Fig 7–Young's modulus in the CD, E_y , as a function of apparent density at different fibre orientation and wet straining levels.

The CD modulus is further decreased by wet straining in the MD. The results for Young's moduli measured mechanically were qualitatively the same as the ultrasonic results. The values of Young's modulus measured mechanically are directly proportional to the moduli measured ultrasonically, essentialy independent of fibre orientation and wet pressing, and are only slightly affected by wet straining.

The tensile strength results, presented in figures 8 and 9, are similar to the results for the moduli except that wet straining has a smaller effect on the tensile strength than on Young's modulus. The observed dependence of the in-plane Young's moduli and tensile strengths on fibre orientation and wet straining is consistent with earlier published work.



Fig 8—MD tensile strength as a function of apparent density at different fibre orientations and wet straining levels.



Fig 9—CD tensile strength as a function of apparent density at different fibre orientations and wet straining levels.

The dependence of the in-plane shear modulus, G_{xy} , on the three variables investigated is shown in figure 10. The three solid lines correspond to the three fibre orientations. G_{xy} decreases with increasing fibre orientation, although the effect is considerably smaller than the changes observed for the inplane Young's moduli. The effect of wet straining on G_{xy} is negligible for the random and slightly orientated sheets, as can be seen from the positions of the open and closed symbols on each line, corresponding to the extremes in wet straining. In the most highly orientated sheet, wet straining slightly decreases the shear modulus (dashed line).

Determination of the in-plane Poisson's ratios has been described elsewhere⁽⁷⁾. The results here will be discussed in terms of the geometric mean of the the two in-plane Poisson's



Fig 10—The in-plane shear modulus, G_{XY} , as a function of apparent density at different fibre orientations and wet straining levels.

Wet strain

ratios, $(\vee_{xy}\vee_{yx})^{1/2}$. The Poisson's ratios were found to be independent of apparent density in the range studied, so averages were calculated for the sheets of different apparent densities. These are presented in Table 3.

Fibre orientation

%	Random	Low	High
0	0.254	0.250	0.200
1.2	0.250	0.269	0.147
2.4	0.260	0.279	0.087



It is evident that the geometric mean of the Poisson's ratios is reasonably constant for both random and slightly orientated sheets at all wet straining levels. For the most highly orientated sheets, however, the geometric mean is smaller, and it is further dramatically reduced with wet straining.

The constancy of the mean Poisson's ratio at random and low fibre orientations, over the range of wet straining studied, agrees with results found earlier in investigations of machine-made papers⁽⁸⁾. In the earlier work, the data for the in-plane elastic constants of machine made papers were found to fit an approximate relationship used to describe other orthotropic systems⁽²⁵⁾,

$$G_{xy} \doteq \frac{1}{2} (E_x E_y)^{1/2} (1 + (v_{xy} v_{yx})^{1/2})$$

This expression is obtained by replacing G, E, and V in the exact expression for an isotropic material, G = E/2(1+V), by the geometric means for E and for the orthotropic material. In the previous work the mean Poisson's ratio was also found to be almost constant, having a mean value for 30 different paper samples of 0.293 with a standard deviation of 0.023. Using this mean value,

$$G_{xy} = 0.387 (E_x E_y)^{1/2}$$

a result which agreed well with (mechanical) data from the literature in which E_x , E_y , and G_{xy} are reported. From the present work it is clear that the mean Poisson's ratio is not constant for all conditions, decreasing significantly at high fibre orientations and wet strains. The approximate relationships above do not apply to the in-plane constants for the highly anisotropic samples.

The data in figure 11 are for the orientated sheets only, and the three lines correspond to the three levels of wet straining.

The z-direction stiffness, C_{33} (which is related to E_z), was measured ultrasonically and was found to be strongly dependent on the apparent density of the sheet, as shown in figure 11. The ZD stiffness does not depend very much on the in-plane fibre orientation. At a constant apparent density, ZD stiffness was reduced by almost 50% by wet straining in the plane of the sheet.





The tensile strength in the thickness direction was measured according to the method developed by Wink and Van Eperen⁽²⁶⁾. The ZD tensile strength is also reduced by wet straining in the plane of the sheet. Although the ZD strength data exhibit more scatter than the ZD modulus data, there is a linear relationship between the z-direction tensile strength and the z-direction stiffness as shown in figure 12. This is analogous to the general relationship found between the tensile strength and Young's modulus in either the MD or CD in the plane of the sheet.



Fig 12-The ZD tensile strength vs. out-of-plane elastic stiffness, C33.

Conclusions

Paper may be thought of as a three-dimensional orthotropic homogeneous continuum as far as wave propagation techniques are concerned, as long as the wavelengths are large with respect to fibre dimensions. The application of orthotropic plate wave theory to paper has improved our understanding of wave propagation in paper and has led to experimental methods for determining the nine orthotropic elastic constants. These constants form a self-consistent set.

Ultrasonic measurements are normally carried out on unstrained samples. We found, however, that if ultrasonic measurements are made on sheets stressed (mechanically) to near failure, the measured elastic constants are essentially the same as those measured in the unstressed sheet (except for corrections of the order of the strain). This suggests that the mechanisms governing the high frequency stress-strain relationships are relatively independent of those phenomena which are important in the usual, long time scale, stress-strain response. Arguments of this type explain the observed differences between `mechanical´ and `ultrasonic´ elastic constants, the latter typically higher by 20 to 30%.

The in-plane and out-of-plane elastic moduli, all measured by ultrasonic techniques. depend on the extent of fibre orientation. the level of wet straining, and the apparent density of the sheet. Increasing fibre orientation or wet straining increases the modulus and tensile strength in the direction of fibre orientation or straining, and concomitantly decreases the corresponding properties in the other two directions. The most dramatic effect of wet straining in the plane occurred in the thickness direction, where a moderate strain of 2.4% resulted in a 50% reduction in the ZD stiffness. On the other hand, unlike the in-plane stiffnesses, the in-plane fibre orientation had little effect on the ZD stiffness. The full importance of these observations will ultimately depend on how important the zdirection properties of paper are in determining the final converting or end use requirements of the material. In any case, it is important to realise that the effects of wet straining in the MD to gain stiffness or strength results in significant decreases in these properties in the CD and ZD.

The in-plane shear modulus, G_{xy} , depends mainly on apparent density. It is reduced somewhat by increasing fibre orientation, but wet straining has no effect on the shear modulus, except at the highest fibre orientation. This observation is unexpected.

The individual in-plane Poisson's ratios, $V_{\chi\gamma}$ and $V_{\gamma\chi}$, are functions of fibre orientation and wet straining. The geometric mean of these, however, is relatively insensitive to fibre orientation and wet straining, at least at the lower levels of each, though its value does decrease significantly at the highest levels of fibre orientation and wet straining. The quantity $(\vee_{xy}\vee_{yx})^{1/2}$, the geometric mean of the in-plane Poisson's ratios, may be thought of as a measure of how `interrelated' the tensions applied in one direction are to the tensions induced in another direction. Although it is conjecture, it would intuitively seem that $(\vee_{xy}\vee_{yx})^{1/2}$ should be related to paper structure. The reduction of this quantity by wet straining at high fibre orientations leads one to suspect some sort of structural damage or bond breakage. However, the stiffness and tensile strength in the MD are still increasing as a result of wet straining.

REFERENCES

- 1. Johnson, J. N., J. Appl. Phys., 1971, 42, 5522.
- Habeger, C.C., Mann, R.W., and Baum, G.A., Ultrasonics, 1979, 17(2), 57.
- Mann, R.W., Baum, G.A., and Habeger, C.C., Tappi, 1979, 62(8), 115.
- Luukkala, M., Heikkila, P., Surakka, J., Ultrasonics, 1971,
 9, 201. 5. Mann R.W., Baum, G.A., and Habeger, C.C., Tappi, 1980, 63(2), 163
- Klason, C., and Kubát, J., Svensk Papperstid., 1976, 79, 494.
- 7. Baum, G.A., and Bornhoeft, L.R., Tappi, 1979, 62(5), 87.
- Baum, G.A., Brennan, D.G., and Habeger, C.C. Submitted to Tappi.
- Theory and Design of Wood and Fiber Composite Materials, (Jayne, B.A., Ed.) Syracuse University Press, 1972.
- 10. Edge, S.R.H., Proc. Tech. Sect. P.M.A., 1945, 26, 425-431.
- 11. Schulz, J.H., Tappi, 1961, 44(10), 736-744.
- 12, Sauret, G., Techniques et Recherches Papetieres, 1963, no. 2, p.3-14. (French).
- 13. Prusas, Z.C., Tappi, 1963, 46(5), 325-330.
- 14. Craver, J.K and Taylor, D.L., Tappi, 1965, 48(3), 142-147

478 orthotropic elastic constants of paper

- Setterholm, V.C., Chilson, W.A., Tappi, 1965, 48(11), 634-640.
- Sauret, G., Chleq, J.P. and Lafabure, G., Technique et Recherches Papetieres, 1965 No. 6, p.30-40 (French)
- Taylor, D.L. and Craver, J.K, in Consolidation of the Paper Web', Vol. 2, p. 852-72, ed. by F. Bolam, London, Tech. Section of the Brit. Paper & Board Makers Ass., Inc., 1966.
- 18. Meyers, G.C., Tappi, 1967, 50(3), 97-100.
- Setterholm, V. and Kuenzi, E.W., Tappi, 1970, 53(10), 1915-20.
- 20. Parsons, S.R., Tappi, 1972, 55(10), 1516-1521.
- 21. Matolesy, G., C.P.P.A. Annual Meeting. (Montreal) 60, Preprints Book B: 19-29 (1974).
- 22. Kimura, M., Karami, Y. Usuda, M. and Kadoya, T., J. Japan Wood Res. Soc. (Mokuzai Gakkaishi), 1978, 24(10), 734-749 (Japanese).
- 23. Sauret, G., Bull. A.T.I.P., 1962, 16(6), 446-454
- 24. Centre Technique de l'Industrie des Papiers, Cartons et Celluloses, French Patent 2,030,715 (Nov. 13, 1970).
- 25. Szilard, R. Theory and Analysis of Plates, pub. by Prentice-Hall Inc. Englewood Cliffs, NJ 1974.
- Wink, W.A. and Van Eperen, R.H., Tappi, 1967, 50(8), 393-400.

Transcription of Discussion

Discussion following paper presented by Dr. G.A. Baum

Dr. H.K. Corte, Wiggins Teape, UK

When a load is applied in any direction parallel to the plane of a sheet of paper, the sheet becomes thicker. Poisson's ratio is negative. How does that agree with your theory?

Dr. G.A. Baum, IPC

Theory gives an absolute value of Poisson's ratio only in the z-direction. We do not believe, however, that Poisson's ratio is negative so long as the deformation remains elastic. If a large enough load is applied then indeed dimensions do change, and there is some evidence to suggest that they do in the way you describe. However, we do not believe this occurs in the elastic regime.

Dr. R.E. Mark, ESPRI, USA

I have two brief questions. Were your sheet orientations measured quantitatively? In your shear wave propagation measurements are your transmitting and/or receiving transducers in physical contact with the sheet?

Dr. G.A. Baum

The answer to both questions is "yes". Fibre orientation distributions were measured quantitatively, though I do not have the values with me here. About 1 or 2% of fibres in the furnish had been dyed black thus allowing us, using an microcomputer with a graphics tablet, to measure the orientation distribution.

Prof. D. Tabor, Cavendish Laboratory, Cambridge, England.

I have two questions to put to you regarding your technique.

Firstly, by using waves of gradually increasing amplitude would it be possible to study the transition from elastic to plastic deformation? Secondly, continuum physics are obviously only applicable to situations where the sample dimensions are considerably greater than the wavelengths in use. Have you tried using very short wavelengths? In solid state physics very interesting things happen when you do.

Dr. G.A. Baum

Taking your second point first, we have not tried using very short wavelengths, though others have, to obtain information at a much finer scale. Referring to the velocity versus frequency curves in our paper, you will see that at about 1-2 MHz velocity begins to fall off, and, according to theory, the generation of surface waves should begin. In practice we found very high attenuation at these frequencies.

On the first suggestion, I do not see an obvious way of doing this in the way you suggest, but the study of the transition can be accomplished in other ways. For example, consider the figure below (figure 2).





It depicts the results of measuring the machine and cross direction extension moduli, and the shear modulus, ultrasonically, while the sample is stretched on an Instron-type tester.

At each of the five points on the curve we measured the three ultrasonic velocities, calculated the appropriate moduli, and expressed them as ratios of the moduli at zero strain.

As strain increases the md modulus increases by about 4 \$ while the value of the tangent to the curve decreases. In the cross direction the modulus decreases by about 1\$, while the shear modulus shows no obvious change.

These results suggest that the mechanisms governing the stress-strain relationships at high frequencies are different from those determining the usual long time constant stress-strain response.

Dr. J.E. Luce, International Paper Company, USA

Could you make a small clarification of the legends on your figure. Do the descriptions md and cd refer to the direction of application of the stress, or was the paper machine made?

Dr. G.A. Baum

We used a machine made commercial paper which was strained in the machine direction while the moduli were measured.

Dr. D.H. Page

I would have said that Dr. Baum's experiment falls into my Class 1, deformation where bond failure does not affect the measurements. I would like to ask two very quick questions. Do you have any measurements of the value of the in-plane Poisson's ratio for well bonded handsheets? Secondly, do you know what value Cox predicts for the Poisson's ratio of a well bonded, random handsheet?

Dr. G.A. Baum

Yes, we have made measurements, and obtained values of about 1/3, in agreement with the theory of Cox and almost all other theories. As discussed in the paper, the geometric mean of 30 values of the in-plane Poisson's ratio, $(v_{xy} v_{yx})^{1/2}$ was 0.29. The majority of samples tested was from machine made commercial paper.